

CLARION® FOOD MACHINERY HT EP  
GREASE, NO. 2

Date 1/09

**DESCRIPTION:** Clarion Food Machinery HT EP Grease, No. 2 is a high temperature, extreme pressure (EP), water resistant grease in an NLGI No. 2 grade. It is registered as an H1 lubricant for incidental food contact by NSF, for use in food plants under the jurisdiction of the U.S.D.A. It meets the requirements of U.S. FDA regulation 21 CFR 178.3570 for lubricants having incidental contact with food.

- QUALITIES:**
- 40 Lb. Timken EP
  - Superior Four-Ball EP and antiwear performance
  - Excellent rust protection
  - Oxidation inhibited
  - Good high-temperature properties
  - Good adhesion/cohesion properties
  - Excellent resistance to the effects of water
  - NSF H1 Registered

**APPLICATIONS:** Clarion Food Machinery HT EP Grease, No. 2 may be used with food processing and packaging machinery where there is a possibility of incidental contact with food.

**CLASSIFICATION:** **NSF H1 - Lubricants with incidental contact (Definition)**  
“These compounds may be used as a lubricant or antirust film on equipment and machine parts in locations in which there is exposure of the lubricated part to edible products. They may also be used as a release agent on gaskets or seals of tank closures. The amount used should be the minimum required to accomplish the desired technical effect on the equipment. If used as an antirust film, the compound must be removed from the equipment surface by washing or wiping as required to leave the surface effectively free of any substance which could be transferred to food being processed.”

(Continued)

CLARION® FOOD MACHINERY HT EP  
GREASE, NO. 2



Date 01/09 - (Continued)

**TYPICAL PROPERTIES:**

**CLARION® FOOD MACHINERY HT EP GREASE, NO. 2**

<b>NLGI No.</b>	<b>2</b>
Material Code	655700009
Thickener	Aluminum Complex
Texture	Smooth, Tacky
Color, Observed	White to Off-White
Worked 60 Penetration, ASTM D 217	265-295
Dropping Point, ASTM D 566, °F (°C)	500 (260) Min.
Wheel Bearing Leakage, ASTM D 1263, % loss	4.5
Water Washout, ASTM D 1264, % loss	7.7 @ 175°F
Water Spray Resistance, ASTM D 4049, % loss	9.2
Rust Prevention, ASTM D 1743, rating	Pass
Copper Corrosion, ASTM D 4048, rating	2A Max.
Oil Separation, ASTM D 1742, % loss	2.0
Timken Test, ASTM D 2509, OK load, lbs	40
Four-Ball Wear, ASTM D 2266, mm scar	0.55
Four-Ball EP Weld Point, ASTM D 2596, kgf	400
Four-Ball Load Wear Index, ASTM D 2596, kgf	55
Approximate Temperature Range, °F (°C)	10 to 325 (-12 to 163)
<b>Characteristics of Oil Plus Oil Soluble Additives:</b>	
Viscosity, ASTM D 445, cSt at 100°C	65.8
ASTM D 445, cSt at 40°C	581
Viscosity Index	188